



AQUAPANEL®

08/2017

AQUAPANEL®

Exterior Basecoat – white

Cement-based reinforcing mortar enhanced with synthetic resin

Description

AQUAPANEL® Exterior Basecoat – white is a cement bound, synthetic resin-enhanced basecoat. It is used for basecoating of AQUAPANEL® Cement Board Outdoor when finishing with a thin layer of decorative render or paint.

Preparation of the substrate

Ensure that the surfaces of the AQUAPANEL® Cement Board Outdoor are dry and dust-free. Ensure that no offsets, open joints or unevenness tolerances are present outside of the required specifications. Make sure the AQUAPANEL® Joint Filler - grey, into which AQUAPANEL® Tape (10 cm) is embedded, is adequately hardened and dry.

Form connections to adjoining building components with suitable sealing tape. Fit plaster stop beads at windows and doors to form the joint to the plaster system. Make sure all external corners have a mesh corner angle fitted.

Mixing

For manual applications, mix contents of 25 kg bag with approx. 6.30 litres of water for approx. 2 minutes. The mixture ratio of powder to water should be in the proportions of 4:1. Allow to settle for approx. 3 minutes and then stir through again for approx. half a minute. Processing time for the mixed plaster is 60 minutes at approx. 20°C.

Process large surface areas using a plaster machine (PFT G4/G5 or equivalent). Add approx. 200 litres of water initially, then adjust to give a lean mortar consistency.

Processing/application

Apply AQUAPANEL® Exterior Basecoat - white 5 mm thick, spread to achieve a flat surface, free from irregularities. Reinforcing strips approx. 30 x 50 cm are placed diagonally from the corners of all building openings. The mesh strips must start directly from the corners beneath the reinforcing mesh. Next, embed AQUAPANEL® Reinforcing Mesh horizontally over the full surface, keeping it free of folds, close to the surface and with 10 cm overlaps. Laying time is approx. 15 min. Open time is approx 20 min at approx 20°C. For plaster layers with grain size < 1 mm or for easy-to-spread felted surfaces, use a 20 cm wide strip of AQUAPANEL® Exterior Reinforcing Tape over the board joints as additional reinforcement. The AQUAPANEL® Tape (10 cm) can then be omitted.

The total dry thickness of the reinforcing layer formed by the AQUAPANEL® Exterior Basecoat - white and AQUAPANEL® Reinforcing Mesh should be a minimum of 4 mm. Before further processing allow a drying time of approximately 24 hours at 20°C. However, this time may be extended depending on temperature and humidity.

Where reinforced mortar surfaces are later to be in contact with banked earth or grit, make sure they are sealed according to current norms and standards after curing and drying to approx. 5 cm above the top edge of the ground contact area.

AQUAPANEL® Exterior Basecoat - white may be processed for further applications. These applications, which are not described in this product information sheet, require technical approval from Knauf Aquapanel.

Material coverage

Base coat with wet layer thickness 5 mm application:
approx. 6.3 kg/m² ≈ 4 m²/bag

Technical data

Reaction to fire	A1
Water absorption	W2
Water vapour diffusion coefficient (table value EN 1745)	μ = 5 (wet cup) μ = 20 (dry cup)
Thermal conductivity λ _{10,dry} table value according to EN 1745	≤ 0.45 W/(mK), P=50% ≤ 0.49 W/(mK), P=90%
Colour	natural white

Working time

Manual: 8 to 10 minutes per m²
Machine: 5 minutes per m²

Working temperature/climate

Do not use when air and/or wall temperatures are below +5°C. Protect fresh plaster from the effects of frost and rapid drying. Protect fresh surfaces from the effects of weathering.

Method of delivery/storage

- 25 kg/bag
- Protect against moisture, storage life 12 months in a dry area. For best quality store in original packaging up until use-by-date - see date printed on packaging.

Item code: 102812

AQUAPANEL®

▶ www.AQUAPANEL.com

@ aquapanel.info@knauf.com

AQUAPANEL® is a technologically advanced building system. Because it's a system, it involves clear step-by-step process from design idea to project completion. AQUAPANEL® cement board panels, accessories and services work in unison – you can be certain that your project will all come together as planned.

AQUAPANEL® is a registered trademark.

Knauf Aquapanel GmbH & Co. KG, Zur Helle 11, 58638 Iserlohn, Germany

All technical changes reserved. Only the current printed instructions are valid. Our warranty is expressly limited to our products in flawless condition. The constructional and structural properties and characteristic building physics of Knauf systems can solely be ensured with the exclusive use of Knauf system components, or other products expressly recommended by Knauf. All application quantities and delivery amounts are based on empirical data that are not easily transferable to other deviating areas. All rights reserved. All amendments, reprints and photocopies, including those of excerpts, require the express permission of Knauf Aquapanel GmbH & Co. KG, Zur Helle 11, 58638 Iserlohn, Germany.